

Material Specification Sheet**Product:**

I36

Description:

A 3.5 mil durable white custom blended polyolefin film facestock.

Recommended Applications:

This material is recommended for a wide variety of inkjet applications requiring durability.

Facestock:

A high strength gloss white Valeron® thermal transfer polyolefin film facestock with a specially formulated coating that has been tested and certified for vertical flame-retardant characteristics.

		<u>Value</u>	<u>Units</u>	<u>Test Method</u>
Caliper:		3.5	mil	ASTM D-374
Tensile:	MD	7,500	lbs/in ²	ASTM D-882
	TD	4,350	lbs/in ²	ASTM D-882
Tear:	MD	75	grams	ASTM D-1992
	TD	215	grams	ASTM D-1992
Elongation:	MD	900	%	ASTM D-412
	TD	815	%	ASTM D-412

Shelf Life:

One year, under standard storage and humidity conditions

PRODUCT DISCLAIMER

All labels and label material constructions are sold with the understanding that the purchaser has independently determined the suitability of each product for the application for which it is purchased. The seller disclaims any implied warranty of fitness of a product for a particular purpose. All materials should be tested thoroughly by the purchaser under end-user conditions to ensure they meet the requirements of a specific application.

