M-292

Smarter Technology. Exceptional Results.

Technical Data Sheet

Description:
An ultra smooth coated facestock with a general purpose removable adhesive and a 40# super calendered bleached kraft stock liner.

Recommended Applications:
For industrial applications requiring high quality barcode printing.

Facestock:
An ultra smooth coated facestock and is TT printable.

		Value	Units	Test Method
Basis Weight:		47.3	lbs/ream ± 5%	
Caliper:		0.0030	inches ± 10%	
Tensile:	MD	27.6	lbs/in width	
	CD	15.6	lbs/In width	
Tear:	MD	46	gms	
	CD	50	gms	
Stiffness:	MD	82	mg	
	CD	49	mg	

Adhesive:
A general purpose removable adhesive.

	Value	Units	Test Method
Minimum Application Temp:	40	°F	
Service Temp Range:	-65 to +180	°F	
Loop Tack:			
Glass	1.0	lbs avg	
Corrugated	0.5	lbs avg	
HDPE	1.0	lbs avg	
Peel Adhesion:			
Glass	0.9	lbs avg	
Corrugated	0.6	lbs avg	
HDPE	0.75	lbs avg	

Liner:
A 40# super calendered bleached kraft stock liner with tear resistance, toughness, and internal strength.

		Value	Units	Test Method
Basis Weight:		41	lbs/ream ± 10%	
Caliper:		0.0025	inches ± 10%	
Tensile:	MD	35	lbs/in width	
	CD	16	lbs/in width	
Tear:	MD	35	gms	
	CD	45	gms	

Shelf Life:
One year under standard storage and humidity conditions. For maximum product longevity, store out of direct sunlight and away from any fumes.

Product Disclaimer: Due to the variety of evolving technologies of OEMs, print engines, press capabilities and inks, all material constructions are sold with the understanding that the purchaser has independently tested and determined the suitability of each product for the application for which it is purchased. The seller disclaims any implied warranty of fitness of a product for a particular purpose. All materials should be tested thoroughly by the purchaser under end-user conditions to ensure they meet the requirements of a specific application.