
Material Specification Sheet**Product:**

M-885

Description:

A clear polyester film facestock that is treated with a non-silicone release and a high-grade emulsion acrylic adhesive.

Recommended Applications:

This material is recommended for applications requiring moisture, chemical, acid, oil, sunlight, weathering, and aging resistance.

Recognized by UL969 and CSA-C22.2 as an overlamine for labels. Meets requirements for 21 CFR 177.1630 and 21 CFR 175.105.

Facestock:

A clear polyester film that is treated with a non-silicone release for smooth controlled unwind.

	<u>Value</u>	<u>Units</u>
Caliper:	0.92	mil

Adhesive:

A high-grade emulsion acrylic adhesive.

	<u>Value</u>	<u>Units</u>
Minimum Application temp:	32	°F
Service temp:	-10 to +300	°F
Caliper:	0.5	mil
Peel:		
Stainless Steel		
30 min. conditioning	13	oz/in
24 hr conditioning	21	oz/in
Loop Tack:	15	oz/in
Haze:	1.3	%
Film Shrinkage: MD	1.6	%
TD	0.7	%
Total Thickness:	1.42	mil

Shelf Life:

One year, under standard storage and humidity conditions

PRODUCT DISCLAIMER

All labels and label material constructions are sold with the understanding that the purchaser has independently determined the suitability of each product for the application for which it is purchased. The seller disclaims any implied warranty of fitness of a product for a particular purpose. All materials should be tested thoroughly by the purchaser under end-user conditions to ensure they meet the requirements of a specific application.

